

RESINKOTE | TECHNICAL DATA SHEET

Azzuro Blue Marble

A mixed light and dark blue marble.



Material profile

Size	2-5 mm
Risk of Staining (RIS)*	
Shape	Rounded
Hardness Value	
Rock Type	Marble

Grading analysis

Sieve Size	% Passing	Range
8.00mm	100	
6.30mm	90	
5.00mm	60	
4.00mm	32	
3.36mm	13	
2.36mm	5	
2.00mm	0	

Physical analysis

Property	Value
Aggregate Abrasion Value (AAV)	12
Aggregate Crushing Value (ACV)	17
Aggregate Impact Value (AIV)	21
Hardness (Moh)	
Magnesium Sulphate Soundness %	1
Polished Stone Value (est) (PSV)	45
Skid Resistant Value (SRV)	
Specific Gravity	
Relative Density (Sat. Surface Dried SSD)	
Relative Density (Apparent) (AP)	2.85
Oil Absorption (% by Weight)	
10% Fines Value (Kn)	
Risk of Iron Staining (est) (RIS)	
Performance Scale	

Chemical analysis

Element	%
Aluminium (Al ₂ O ₃)	0.07
Calcium (CaO)	30.8
Calcium Carbonate (CaCO ₃)	
Iron (Fe ₂ O ₃)	0.04
Magnesium (MgO)	21.37
Magnesium Carbonate (MgCO ₃)	
Manganese (MnO)	
Phosphorus (P ₂ O ₅)	0.01
Potassium (K ₂ O)	<0.01
Silica (SiO ₂)	0.16
Sodium (Na ₂ O)	<0.01
Sulphate (SO ₃)	0.02
Titanium (TiO ₂)	<0.01
Loss of Ignition	47.14

Risk of Staining (RIS)*

- ★ No likelihood of any rust staining. ★★ No previous recorded instances of rust staining within this product.
- ★★★ Potential for rust staining within this rock type with recorded instances.

Need product or specification support?

Practical advice and project support across Australia.

1300 752 956