

RESINKOTE | TECHNICAL DATA SHEET

Rhine Gold

Pale **golden and bronze** aggregate.



Material profile

Size	2-5 mm
Risk of Staining (RIS)*	★★
Shape	Rounded
Hardness Value	6
Rock Type	Quartz

Grading analysis

Sieve Size	% Passing	Range
8.00mm	100	100
6.30mm	93	80-100
4.75mm	53	20-90
3.35mm	14	5-55
2.36mm	3	0-10

Physical analysis

Property	Value
Aggregate Abrasion Value (AAV)	1
Aggregate Crushing Value (ACV)	18
Aggregate Impact Value (AIV)	19
Hardness (Moh)	7
Magnesium Sulphate Soundness %	2
Polished Stone Value (est) (PSV)	44
Skid Resistant Value (SRV)	
Specific Gravity	
Relative Density (Sat. Surface Dried SSD)	2.58
Relative Density (Apparent) (AP)	2.62
Oil Absorption (% by Weight)	
10% Fines Value (Kn)	
Risk of Iron Staining (est) (RIS)	★★
Performance Scale	

Chemical analysis (typical)

Element	%
Aluminium (Al ₂ O ₃)	3.07
Calcium (CaO)	<0.01
Calcium Carbonate (CaCO ₃)	
Iron (Fe ₂ O ₃)	1.77
Magnesium (MgO)	0.41
Magnesium Carbonate (MgCO ₃)	
Manganese (MnO)	
Phosphorus (P ₂ O ₅)	0.03
Potassium (K ₂ O)	0.44
Silica (SiO ₂)	92.06
Sodium (Na ₂ O)	0.14
Sulphate (SO ₃)	<0.01
Titanium (TiO ₂)	0.2
Loss of Ignition	1.10

Risk of Staining (RIS)*

- ★ No likelihood of any rust staining.
- ★★ No previous recorded instances of rust staining within this product.
- ★★★ Potential for rust staining within this rock type with recorded instances.

Need product or specification support?

Practical advice and project support across Australia.

1300 752 956