

RESINKOTE | TECHNICAL DATA SHEET

Winter Quartz

A creamy white angular chipping with flecks of cream, yellow and grey.



Material profile

Size	2-5 mm
Risk of Staining (RIS)*	★★
Shape	Angular
Hardness Value	7
Rock Type	Quartz

Grading analysis

Sieve Size	% Passing	Range
8.00mm	100	100
6.30mm	90	80-100
4.75mm	48	20-90
3.35mm	5	5-55
2.36mm	0	0-10

Physical analysis

Property	Value
Aggregate Abrasion Value (AAV)	0.6
Aggregate Crushing Value (ACV)	24
Aggregate Impact Value (AIV)	49
Hardness (Moh)	7
Magnesium Sulphate Soundness %	13
Polished Stone Value (est) (PSV)	54
Skid Resistant Value (SRV)	65
Specific Gravity	
Relative Density (Sat. Surface Dried SSD)	2.58
Relative Density (Apparent) (AP)	2.62
Oil Absorption (% by Weight)	0.90
10% Fines Value (Kn)	
Risk of Iron Staining (est) (RIS)	★★
Performance Scale	

Chemical analysis (typical)

Element	%
Aluminium (Al ₂ O ₃)	0.13
Calcium (CaO)	0.01
Calcium Carbonate (CaCO ₃)	
Iron (Fe ₂ O ₃)	0.01
Magnesium (MgO)	0.03
Magnesium Carbonate (MgCO ₃)	
Manganese (MnO)	0.01
Phosphorus (P ₂ O ₅)	0.02
Potassium (K ₂ O)	<0.01
Silica (SiO ₂)	99.24
Sodium (Na ₂ O)	<0.05
Sulphate (SO ₃)	<0.01
Titanium (TiO ₂)	0.02
Loss of Ignition	0.3

Risk of Staining (RIS)*

- ★ No likelihood of any rust staining.
- ★★ No previous recorded instances of rust staining within this product.
- ★★★ Potential for rust staining within this rock type with recorded instances.

Need product or specification support?

Practical advice and project support across Australia.

1300 752 956